

MATERIAL DATA SHEET

Material type: Silicon Carbide

SC140A
Properties of Microstructure

Alumina Content		%	-
Density	JIS R 1634	g/cm ³	3.1
Water Absorption		%	0
Mean Grain Size		µm	-

Mechanical Properties

Hardness (HV 9.807N)	JIS R 1610	GPa	23
Compressive strength	JIS R 1608	MPa	-
Flexural strength	JIS R 1601	MPa	500
Modulus of Elasticity	JIS R 1602	GPa	430
Poisson's ratio	JIS R 1602		-
Fracture toughness	JIS R 1607	MPa*m ^{1/2}	-

Thermal Properties

Specific Heat 20°C	JIS R 1611	J/gK	-
Thermal Conductivity	JIS R 1611	W/mK	181
Expansion coefficient 40-400°C	JIS R 1618	10 ⁻⁶ /K	3.7
Expansion coefficient 40-800°C	JIS R 1618	10 ⁻⁶ /K	-
Thermal Shock Temperature Difference (in water)	JIS R 1648	°C	-

Electrical Properties

Dielectric strength	JIS C 2141	kV/mm	10 ⁶
Specific Resistance 20°C	JIS C 2141	Ω•cm	-
Specific Resistance 300°C	JIS C 2141	Ω•cm	-
Specific Resistance 500°C	JIS C 2141	Ω•cm	-
Dielectric constant (1 MHz)	JIS C 2141		-
Dielectric Loss Angle (1 MHz)	JIS C 2141	10 ⁻⁴	-
Typical Colour			-

The values are typical material properties and may vary according to products configuration and manufacturing process.